


































ADAGIO Alpha⁺ Mineral ceiling



- ADAGIO Alpha⁺ offers a smooth, uniform, and durable surface with unparalleled scratch resistance and the brightest white visual available. The tile also provides a balance of both sound absorption and sound attenuation, as well as high light reflectance.
- Excellent sound absorption: 1.00 α_w .
- Excellent Light Reflectance: 88%.
- ISO 4, Indoor Air Comfort Gold and Cradle to Cradle Certified® Bronze.
- Ideal for open spaces
(call centres, libraries, open space offices, cafeterias, etc.).

Build on us.



Characteristics	Detailed information						
Edge details 	Board 	Tegular 24/90 			Tegular 15/90 		
Thickness (mm) 	20		20			20	
Dimensions (mm) 	600 x 600 625 x 625 675 x 675 1200 x 300 1200 x 600 1250 x 625 1500 x 600 1800 x 600		600 x 600 625 x 625 675 x 675 1200 x 300 1200 x 600 1250 x 625 1500 x 600 1800 x 600			600 x 600 625 x 625 675 x 675 1200 x 300 1200 x 600 1250 x 625 1350 x 300 1350 x 600 1500 x 600 1800 x 600	
System 	Exposed demountable - System C					Exposed demountable - System C Exposed - Bandraster, demountable - System I.3 Exposed - Corridor, demountable - System F.3	
Weight 	3.4 kg / m ²						
Colour 	 White						
Sound absorption 	EN ISO 354 $\alpha_w = 1.00$ as per EN ISO 11654 - Class A						
	Frequency f (Hz)	125	250	500	1000	2000	4000
	α_p	0.55	0.80	1.00	0.95	1.00	1.00
NRC = 0.95 as per ASTM C 423							
Sound attenuation 	EN ISO 10848-2 D _{n,f,w} = 25 dB as per EN ISO 717-1 CAC = 26 dB as per ASTM E 413-10						
Sound reduction 	EN ISO 10140-2 R _w = 12 dB as per EN ISO 717-1						
Fire reaction 	Euroclass A2-s1, d0 as per EN 13501-1						
Light reflectance 	88%						
Thermal conductivity 	$\lambda = 0.040$ W/mk as per EN 12667						
Air permeability 	PM3 (≤ 100 m ³ /hm ²) as per DIN 18177						
Humidity resistance 	95% RH						
Clean room 	ISO 4 as per EN ISO 14644-1						
Indoor air quality 	 A+	 E1	 IACG				
Cleanability 							
Sustainability 	 EN ISO 14021 59.6% (2024)	 BIOSOLUBLE WOOL EC 1272/2008 Annex Q	 M1+ GREEN STAR EMISSION CLASS FOR BUILDING MATERIALS	 certified cradle to cradle BRONZE	 www.blauer-engel.de/uz132		